

12 STRAND ROPE

			DAN-STRONG PP ROPE		POLYAMIDE NYLON		AOXI FLEXI POLYESTER		SUPER FLEX PP/PES		MAXI FLEX PP/PES	
Dia (mtm)	Dia (Inch)	Cir (Inch)	Wt. per 220 Mtrs in kgs.	MBL Kgf	Wt. per 220 Mtrs in kgs.	MBL Kgf	Wt. per 220 Mtrs in kgs.	MBL Kgf	Wt. per 220 Mtrs in kgs.	MBL Kgf	Wt. per 220 Mtrs in kgs.	MBL Kgf
52	2-1/16	6-1/2	274.00	45750	387.00	49000	451.00	45000	327.00	55500	276.00	45800
56	2-1/4	7	316.00	52000	449.00	56000	524.00	51500	371.00	63200	321.00	52400
60	2-3/8	7-1/2	364.00	59500	512.00	64000	600.00	58500	417.00	72400	370.00	60000
64	2-1/2	8	413.00	67550	579.00	72000	684.20	66600	463.00	81600	419.00	67900
68	2-15/16	8-1/2	470.00	76000	666.00	81000	772.20	74400	540.00	91800	474.00	76700
72	2-7/8	9	523.00	84500	739.00	90000	864.60	83000	586.00	102000	530.00	85200
76	3	9-1/2	586.00	94000	822.00	100000	965.80	92500	692.00	112000	576.50	95064
80	3-5/32	10	648.00	104000	913.00	110000	1,067.00	102000	765.00	125000	657.00	105000
84	3-1/2	10-1/2	716.00	114000	1,000.00	120000	1,179.00	112000	768.90	136500	704.11	115500
88	3-7/16	11	787.00	125000	1,100.00	131000	1,292.00	122000	912.00	148000	793.00	126000
96	3-13/16	12	934.00	148000	1,339.00	154000	1,537.00	144000	1,075.00	174000	944.00	149000
104	4-1/2	13	1,095.00	169500	-	-	-	167000	1,237.00	198300	110.00	170000

Note: The Tensil mentioned is of unspliced ropes